

## Spoon Rest Firing Schedule

This is the schedule that I use for 96 glass on the Creative Paradise GM181 mold with two layers of 1/8" glass.



Seg	DPH	Temp	Hold
1	300	1200	30
2	300	1250	35
3	AFAP	950	55
4	200	750	0

Total running time: 7.38 hours. approx. Dumping heat at 1250 may alter time.